



# GORE® Joint Sealant DF



## Gasket for large diameter flanges OUTSTANDING SEALING RELIABILITY

GORE® Joint Sealant DF is engineered for the reliable sealing of large, complex or damaged flanges.

GORE® Joint Sealant DF is made from virgin, mono-directionally expanded PTFE (ePTFE). After compression this gasketing material forms a thin sealing film that is highly resistant to creep and cold flow. This produces a durable gasket which reduces the risk of leakage, unplanned downtime and loss of output.

Installation of GORE® Joint Sealant DF is extremely easy. The gasket is simply stuck onto the flange surface with the ends overlapped. Time spent on installation is thus reduced to a minimum.

The GORE® Joint Sealant DF ensures an effective, enduring, and cost-effective seal, making a valuable contribution towards keeping your production and manufacturing processes optimised.

### TECHNICAL DATA

#### MATERIAL

100% expanded PTFE (ePTFE) with monodirectionally oriented fibril structure.

#### TEMPERATURE RANGE OF THE MATERIAL

-268 °C to +315 °C / -450 °F to +600 °F

#### CHEMICAL RESISTANCE

Resistant to all media (pH 0 – 14), except for molten or dissolved alkali metals and elemental fluorine particularly at high temperatures and pressures.

#### STABILITY

Not subject to ageing within the material's temperature range, UV-resistant and can be stored indefinitely. Storage of more than 12 months after delivery of the product may result in decline of adhesive strength.


#### PHYSIOLOGICAL SAFETY

Physiologically harmless within temperature range of material.  
FOR INDUSTRIAL USE ONLY.

Not for use in food, drug, cosmetic or medical device manufacturing, processing, or packaging operations.

#### OPERATING RANGE

The maximum applicable pressure as well as the maximum safe operating temperature depend mainly on the equipment. Standard pressures range from full vacuum to 40 bar.



### KEY FEATURES

- 100% expanded PTFE (ePTFE)
- Chemically resistant
- Temperature resistant
- Resistant to creep and cold flow

### KEY BENEFITS

- Reliable sealing performance
- Supports process optimization
- Wide range of applications, can be used with virtually any media
- Easy to install
- No wasteful scrap

### TYPICAL APPLICATIONS

- Large and complex flange dimensions
- Damaged flanges
- Aggressive media


### TESTS AND CERTIFICATES

- EN 13555
- BAM
- TA Luft
- DVGW





# GORE® Joint Sealant DF



## AVAILABLE SIZES AND SIZE SELECTION

Type	Nominal Width [mm]	Length Per Spool [m]				For Effective Sealing Width [mm]
		5	10	25	50	
DF01*	1			✓	✓	
DF03	3		✓	✓	✓	3-7
DF05	5		✓	✓	✓	7-10
DF07	7		✓	✓	✓	10-17
DF10	10		✓	✓	✓	17-25
DF14	14		✓	✓	✓	25-40
DF17	17	✓	✓	✓		40-50
DF20	20	✓	✓	✓		50-65
DF25	25	✓	✓			65+

\* Not supplied with an adhesive backing strip.

## INSTALLATION LINE FORCE FOR LEAKAGE CLASS L<sub>0.1</sub>

Type	DF03	DF05	DF07	DF10	DF14	DF17	DF20
Q* <sub>min(0.1)</sub> [N/mm]	95	139	181	252	336	418	431

Test following EN 13555.

Our technical bulletins about the product provide further details.

In order to get the required installation force, simply multiply the line force with the length of the GORE® Joint Sealant DF.

## OTHER TESTS

GORE® Joint Sealant DF has been tested by BAM (Bundesanstalt für Materialforschung und -prüfung) for application with oxygen. It is suitable for use in applications with gaseous oxygen at a maximum pressure of 40 bar and a maximum temperature of 60 °C. The gasket has also been tested by DVGW (Deutscher Verein des Gas- und Wasserfaches e.V.).

For detailed information and test reports, please contact your local Gore representative.

Gasket Parameters/USA

m = 1.5 Y = 2500 psi

## QUALITY ASSURANCE

The GORE Quality Management System has been certified by DQS in accordance with ISO 9001. Component suppliers are also integrated into this system.



## ORDERING TEXT

GORE® Joint Sealant DF, width (mm), spool length (m), number of units

Supplied by: \_\_\_\_\_

For detailed selection criteria, technical information, installation guideline and a complete listing of local sales offices please visit [gore.com/sealants](http://gore.com/sealants)

**North America/South America**  
**W. L. Gore & Associates Inc. (USA)**  
 Tel.: +1 800 654-4229  
 Fax: +1 410 506-8585  
 Email: [sealants@wlgore.com](mailto:sealants@wlgore.com)

**Europe/Middle East/Russia/Africa**  
**W. L. Gore & Associates GmbH (Germany)**  
 Tel.: +49 89 4612-2215  
 Fax: +49 89 4612-43780  
 Email: [sealants\\_EU@wlgore.com](mailto:sealants_EU@wlgore.com)

**Asia/Australia**  
**W. L. Gore & Associates (China)**  
 Tel.: +86 21 6247-1999  
 Fax: +86 21 6247-9199  
 Email: [sealants\\_AP@wlgore.com](mailto:sealants_AP@wlgore.com)

All technical information and advice given here is based on our previous experiences and/or test results. We give this information to the best of our knowledge, but assume no legal responsibility. Customers are asked to check the suitability and usability in the specific application, since the performance of the product can only be judged when all necessary operating data are available. Specifications are subject to change without notice. Gore's terms and conditions of sale apply to the purchase and sale of the product.

GORE and designs are registered trademarks of W. L. Gore & Associates, © 2010, W. L. Gore & Associates, Inc.

